

Please amend the application as follows:

In the Claims:

Cancel Claims 1, 2, 5 and 24-25, without prejudice.

1. (Canceled)

2. (Canceled)

3. (Previously Canceled)

4. (Withdrawn)

5. (Canceled)

6-9. (Previously Canceled)

10. (Previously Amended) The adsorption powder according to Claim ~~6~~ 34, wherein the powder comprises from about 35 to about 45 weight percent of carbon-based powder, from about 50 to about 65 weight percent of calcium hydroxide, from about 2 to about 8 weight percent of sulfur, and from about to about 12 weight percent of cupric chloride, based on 100 total weight percent.

11-19. (Previously Canceled)

20. (Previously Amended) The adsorption powder according to Claim ~~5~~ 35, wherein the powder comprises from about 10 to about 45 weight percent of potassium iodide impregnated onto a carbon substrate, from about 45 to about 55 weight percent of calcium

hydroxide, and from about 10.1 to about 45 weight percent of cupric chloride, based on 100 total weight percent.

21. (Previously Canceled)

22. (Original) The adsorption powder according to Claim 20, wherein the powder comprises about 10 weight percent of potassium iodide impregnated onto a carbon substrate, about 45 weight percent of calcium hydroxide, and about 45 weight percent of cupric chloride.

23. (Previously Canceled)

24. (Canceled)

25. (Canceled)

26. (Previously Added) An adsorption powder suitable for removing metals and organic compounds from gas streams, comprising from about 25 to about 45 weight percent of carbon-based powder, from about 45 to about 60 weight percent of calcium hydroxide, from about 1 to about 15 weight percent of potassium iodide impregnate onto a carbon substrate, and from about 1 to about 10 weight percent of cupric chloride, based on 100 total weight percent.

27. (Currently amended) ~~An~~ The adsorption powder suitable for removing metals and organic compounds from gas streams according to Claim 26, comprising from about 30 to about 40 weight percent of carbon-based powder, from about 50 to about 55 weight percent of calcium hydroxide, from about 5 to about 10 weight percent of potassium iodide impregnate onto a carbon substrate, and from about 5 to about 10 weight percent of cupric chloride, based on 100 total weight percent.

28. (Currently amended) ~~An~~ The adsorption powder ~~suitable for removing metals and organic compounds from gas streams~~ according to Claim 26, comprising about 35 weight percent of carbon-based powder, about 55 weight percent of calcium hydroxide, about 5 weight percent of potassium iodide impregnated onto a carbon substrate, and about 5 weight percent of cupric chloride.

29. (Currently amended) ~~An~~ The adsorption powder ~~suitable for removing metals and organic compounds from gas streams~~ according to Claim 26, comprising about 35 weight percent of carbon-based powder, about 50 weight percent of calcium hydroxide, about 10 weight percent of potassium iodide impregnated onto a carbon substrate, and about 5 weight percent of cupric chloride.

30. (Previously Added) An adsorption powder suitable for removing metals and organic compounds from gas streams, comprising about 10 to about 45 weight percent of potassium iodide impregnated onto a carbon substrate, from about 45 to about 55 weight percent of calcium hydroxide, and from about 1 to about 45 weight percent of cupric chloride, based on 100 total weight percent.

31. (Currently amended) ~~An~~ adsorption powder suitable for removing metals and organic compounds from gas streams according to Claim 30, comprising about 38 weight percent of potassium iodide impregnated onto a carbon substrate, about 52 weight percent of calcium hydroxide, and about 10 weight percent of cupric chloride.

32. (Currently amended) ~~An~~ The adsorption powder ~~suitable for removing metals and organic compounds from gas streams~~ according to Claim 30, comprising about 10 weight percent of potassium iodide impregnated onto a carbon substrate, about 45 weight percent of calcium hydroxide, and about 45 weight percent of cupric chloride.

33. (Currently amended) ~~An~~ The adsorption powder ~~suitable for removing metals and organic compounds from gas streams~~ according to Claim 30, comprising about 10 weight percent of potassium iodide impregnated onto a carbon substrate, about 30 weight percent of activated carbon, about 50 weight percent of calcium hydroxide, and about 10 weight percent of cupric chloride.

34. (Previously Added) An adsorption powder suitable for removing metals and organic compounds from gas streams, wherein the powder comprises from about 10 to about 60 weight percent of carbon-based powder, from about 10 to about 70 weight percent of calcium hydroxide, and from at least about 10.1 to about 45 weight percent of cupric chloride, based on 100 total weight percent.

35. (Previously Added) An adsorption powder suitable for removing metals and organic compounds from gas streams, wherein the powder comprises, wherein the powder comprises from about 25 to about 45 weight percent of carbon-based powder, from about 40 to about 60 weight percent of calcium hydroxide, from about 2 to about 10 weight percent of sulfur, from about 5 to about 15 weight percent of potassium permanganate, and from about 10.1 to about 15 weight percent of cupric chloride, based on 100 total weight percent.